



ENRICH PULP AND PAPER

TODAY • TOMORROW • FOREVER

SPECIFICATIONS

LEO LINER						
STANDARD	BURST FACTOR	RCT (CD)		COBB 60 Second (gm/m ²)		MOISTURE
GSM	RANGE	Min	Max	Top	Bottom	%
140 ± 5%	28 - 35	1.2	1.5	40	50	6.0 - 8.0
150 ± 5%	28 - 35	1.3	1.8	40	50	6.0 - 8.0
180 ± 5%	28 - 35	1.7	2.2	40	50	6.0 - 8.0
200 ± 5%	28 - 35	2	2.4	40	50	6.0 - 8.0
220 ± 5%	28 - 35	2.1	2.5	40	50	6.0 - 8.0
250 ± 5%	28 - 35	2.4	2.8	40	50	7.0 - 8.0
300 ± 5%	28 - 35	2.8	3.5	40	50	7.0 - 8.0
350 ± 5%	28 - 35	3.2	4	40	50	7.0 - 8.0

SPECIFICATIONS

LEO FLUTE					
STANDARD	BURST FACTOR	RCT (CD)		COBB 60 Second (gm/m ²)	MOISTURE
GSM	RANGE	kn/m	kg/f	Top	%
80 ± 3	18 - 20	0.4	5.4	40	8 ± 2
90 ± 3	18 - 20	0.4	6.2	40	8 ± 2
100 ± 4	18 - 20	0.6	8.5	40	8 ± 2
110 ± 5	18 - 20	0.7	10	40	8 ± 2
125 ± 6	18 - 20	0.7	10	40	8 ± 2
140 ± 6	18 - 20	1	15.5	40	8 ± 2
150 ± 6	18 - 20	1.1	17	40	8 ± 2
175 ± 5%	18 - 20	1.3	20	40	8 ± 2

NOTE

1. All Properties are according to Laboratory testing at Enrich Papers.
2. This specification can be improved further, subject to product upgradation.
3. Test Climate -
Temperature : 23°C ± 1°
Relative Humidity : 50% ± 5

